

Péto  
Baraka  
LUBRIFIANT



Péto  
Baraka  
LUBRIFIANT

**PERFORMANCE**

**SAE 0W30**

**ADVANCED  
PRO**



Huile moteur 

**PERFORMANCE**

**NORMES INTERNATIONALE**

**ACEA C3**

**API SP**



**HOMOLOGATION**

- MB-APPROVAL 229.31 / 229.51 / 229.52
- VW 504 00 / 507 00
- VW TL 52545
- PORSCHE C30
- BMW LONGLIFE - 04



**GAMME  
SYNTHÉTIQUE  
QUAD**

**حكاية ثقة..**

## PERFORMANCE

PB-9390

SAE 0W30

ADVANCED  
PRO



## DESCRIPTION

**PERFORMANCE ADVANCED PRO PB-9390** is a 100% synthetic lubricant that benefits from the latest technological innovations in engine lubrication. It provides an exceptional level of mechanical protection while perfectly combining high performance with fuel economy.

Its enhanced oxidation resistance allows for extended oil drain intervals as recommended by the Volkswagen Group (Volkswagen, Audi, SEAT, and Skoda).

## APPLICATION

**PERFORMANCE ADVANCED PRO PB-9390** is suitable for gasoline and diesel vehicles for which the manufacturer recommends a lubricant meeting ACEA C3 and API SP specifications.

It is specifically designed to meet the latest requirements of modern engines where an SAE 0W-30, ACEA C3 engine oil is specified.

### PERFORMANCES :

- Normes Internationales
- ACEA C3
- API SP

### Homologations :

- MB-Approval 229.31
- MB-Approval 229.51
- MB-Approval 229.52
- VW 504 00 / 507 00
- VW TL 52545
- Porsche C30
- BMW Longlife-04

## CLIENT BENEFITS

- Enhanced oxidation resistance, ensuring maximum oil drain intervals as recommended by the Volkswagen Group (Volkswagen, Audi, SEAT, and Škoda).
- Excellent fluidity and a strong oil film, even at very low temperatures.
- Outstanding shear stability, maintaining optimal lubrication at high operating temperatures.
- Reduced environmental impact and a significant decrease in CO<sub>2</sub> and NO<sub>x</sub> emissions.

## PERFORMANCE

PB-9390

SAE 0W30

ADVANCED  
PRO



## TYPICAL CHARACTERISTIC

These values are typical of current production. However, Pétro Baraka reserves the right to modify certain characteristics in accordance with the product's conformity to its specifications.

Test	Test Methods	Units	Result
SAE Viscosity Grade	SAE J300	-	0W30
Density at 15 °C	ASTM D 4052	-	0,847
Kinematic Viscosity at 40 °C	ASTM D 445	mm <sup>2</sup> /s	60,6
Kinematic Viscosity at 100 °C	ASTM D 445	mm <sup>2</sup> /s	12,1
Viscosity Index	ASTM D 2270	-	201
Pour Point	ASTM D 97	°C	-51
Flash Point	ASTM D 92	°C	240
Total Base Number (TBN)	ASTM D 2896	(mg KOH/g)	7,8

## STORAGE CONDITIONS

Do not store products at temperatures above 60°C. It must be stored away from direct sunlight, intense cold and external temperature fluctuations. If possible, the packaging should never be exposed to weather. Otherwise, the drums shall be placed horizontally, so as to avoid contamination by water and to preserve the product label.

**Pétro  
Baraka**

   **PétroBaraka**  
 [www.petrobaraka.com](http://www.petrobaraka.com)  
[contact@petrobaraka.com](mailto:contact@petrobaraka.com)



**رمز الثقة**  
**SYMBOLE DE CONFIANCE**  
منتج وموزع من طرف شركة ذ م م بيترو بركة  
Oued zmor, la route nationale n46 Lot n01, Biskra  
+213 (0) 33 55 27 11, 12